

IN THE CLAIMS

Please cancel Claims 2 and 4, without prejudice.

Please amend the claims as follows:

1. (Currently Amended) An aqueous nanoparticle ceramic agglomerate dispersion, for forming an ink-absorbing layer of an ink-jet recording medium, comprising:

- a nanoparticle ceramic agglomerate dispersed in deionized water;
- said nanoparticle ceramic agglomerate having an average diameter of 0.05 to 0.3 μm

at a viscosity suitable for coating of 10 to 200 mPa·s as measured by a laser diffraction particle size distribution measurement apparatus, at a viscosity suitable for coating of 10 to 200 mPa·s as measured at 22°C at 2.5 rpm using a E-type viscometer and

- said nanoparticle ceramic agglomerate having a size distribution curve such that the ratio of peak width at a height which is half the maximum height of said curve, determined according to the results of said measurement, to the maximum height is 0.7 or less;

- said dispersion having been prepared by ultra-high pressure counter jet streams of the dispersion colliding with each other.

2. (Cancelled)

3. (Withdrawn) An ink-jet recording medium having an ink-absorbing layer deposited on a surface thereof produced from the aqueous nanoparticle ceramic agglomerate dispersion of claim 1.

4. (Cancelled)

5. (Withdrawn) The ink-jet recording medium according to claim 3 wherein said dispersion further contains a cationic polymer.

6. (Withdrawn) The ink-jet recording medium according to claim 3 wherein said surface is a water absorbing paper recording surface.

7. (Withdrawn) A method of making an ink jet recording medium comprising applying to a recording surface a coating of the aqueous nanoparticle ceramic agglomerate dispersion of claim 1, cooling the coating, and drying the coating to produce said recording medium.

8. (Withdrawn) The method according to claim 7 wherein said recording surface is a water absorbing papers.

9. (Withdrawn) The method according to claim 7 wherein said dispersion also contains a cationic polymer.

10. (Previously Added) The aqueous nanoparticle ceramic agglomerate dispersion according to claim 1, wherein the nanoparticle ceramic agglomerate is a member selected from the group consisting of SiO_2 , Al_2O_3 , and TiO_2 .

11. (Previously Added) The aqueous nanoparticle ceramic agglomerate dispersion according to claim 1, wherein the aqueous nanoparticle ceramic agglomerate dispersion is made by subjecting nanoparticle ceramic agglomerates to treatment in a jet mill apparatus in which counter jet streams of the dispersion collide with each other at a jet stream radius of 0.1 mm at a collision position, at a jet stream velocity 600 m/sec and a flow rate of the jet stream at the

B¹
nozzles of 15 liters per minute for a predetermined time to disintegrate the nanoparticle ceramic agglomerates.

12. (New) A nanoparticle ceramic agglomerate having an average diameter of 0.05 to 0.3 μm as measured by a laser diffraction particle size distribution measurement apparatus, and a size distribution curve such that the ratio of peak width at a height which is half the maximum height of said curve, determined according to the results of said measurement, to the maximum height is 0.7 or less.

13. (New) A method of making an ink-jet recording medium comprising depositing on said medium the aqueous dispersion of claim 1.

B²
14. (New) An aqueous dispersion comprising a cationic polymer and nanoparticle ceramic agglomerates having an average diameter of 0.05 to 0.3 μm as measured by a laser diffraction particle size distribution measurement apparatus, and a size distribution curve such that the ratio of peak width at a height which is half the maximum height of said curve, determined according to the results of said measurement, to the maximum height is 0.7 or less.

15. (New) A method of making an aqueous dispersion comprising dispersing nanoparticle ceramic agglomerates in water to thereby form an aqueous dispersion and subjecting the resulting dispersion to a jet mill in which counter jet streams of the dispersion are collided with each other.

16. (New) The method according to claim 15 wherein the jet stream has a radius of 0.1mm, velocity of 600 m/sec and a flow rate of 15 liters/minute.

17. (New) Paper for inkjet printing having deposited thereon a coating resulting from the aqueous dispersion according to claim 1.

B² 18. (New) The paper according to claim 17 having a color image printed thereon.

19. (New) The aqueous dispersion according to claim 1 wherein the ceramic is a member selected from the group consisting of silica, alumina and titania.

20. (New) The aqueous dispersion according to claim 19, wherein the ceramic is prepared by gas phase hydrolysis.
